


Prisma

Natural Simulation Aesthetic Zirconia


Innate radiance,
unveiled true beauty




Indications



Prisma (1-3 unit) bridge sintering curve



Prisma (4-6 unit) bridge sintering curve



Physical Characteristics

Sintered Density	6.07±0.03g/cm ³
Bending Strength	700-1050MPa(Av.)
Transmittance	57%-43%
Hardness	1200HV
Sintering Temperature	1530°C



Adaptation Systems



Color

